

CS 2K Clear VOC Premium

2K clear coat

:: CHARACTERISTIC

The CS 2K Clear Premium is easy to handle, has excellent flow properties and a brilliant gloss. Due to its excellent drying properties it can be polished easily with our paint finish products. With this clear coat the user can exhaust the complete spectrum of possibilities, from single components to complete paintwork. Additionally it is exceptional scratch resistance combined with a very high UV-protection.

:: APPLICATION

This VOC-conform 2K clear coat is suitable for application on small parts as well as on complete paintwork like full vehicle fronts.

:: PRODUCT DATA









MATERIAL DATA



| | |
|-----------------------------|---|
| Colour clear coat: | Transparent |
| V.O.C.: | 2004/42/IIIB(d)(420) < 420 g/l |
| Shelf life: | 18 month in closed original container at 20°C |
| Density clear coat at 20°C: | 0.98 - 0.99 g/cm ³ |
| Density hardener at 20°C: | 1.00 - 1.05 g/cm ³ |
| Dry film thickness: | 50 - 60 µm |
| Efficiency: | 11 – 12 m ² /l |

:: HANDLING

For application on solvent- or water-based primer and Uni-Topcoats. It is strongly recommended to work with the complete system. Drying and adhesion problems cannot be excluded with use of thinning and hardening materials of external systems.

Clear coat has to be reworked 2 hours after application at the latest.

| MIXING RATIO | | |
|---|--|--|
|  | 2K Clear VOC Premium 2K Hardener VOC Premium Thinner High Gloss Additive | by volume |
| | | 2 1 0 - 10% vol. on component A 5 - 8% vol. on component A |
| | 2K Clear VOC Premium 2K Hardener standard 2K Hardener fast 2K Hardener slow Thinner High Gloss Additive | by weight |
| | | 100 g 51 g 52 g 53 g 0 - 9% wt. on component A 4 - 7% wt. on component A |
| SPRAYING VISCOSITY | | |
|  | DIN cup 4mm at 20°C Ford cup 4mm at 20°C ISO cup 4mm at 20°C | 18 - 22 seconds 19 - 23 seconds 42 - 50 seconds |
| APPLICATION | | |
|  | Spray gun gravity feed | Nozzle size / pressure Nozzle size: 1,2mm Air pressure: Please pay attention to operating pressure recommendations of the manufacturer. |
|  | Application | 2 spraying operations 2 coats |
|  | Pot life at 20°C | 40 min with hardener standard 40 min with hardener fast 50 min with hardener slow |
|  | Flash off | 7 - 10 minutes between coats 10 minutes before baking |
|  | Dry coat thickness | 50 - 60 µm |
|  | Process conditions | Temperature 18 - 22°C Relative air humidity 40 - 60% |

| PROCESSING | | | |
|--|-------------------------|---|--|
| | Object temperature | 20°C | 60°C |
| | |  <p> Hardener standard Hardener fast Hardener slow Full hardness </p> | <p>9 - 10 h 6 - 8 h 11 - 12 h 7 days</p> |
| NOTE: Prior to polishing the clear coat dried at 60°C, wait up to 1h for cooling down. | | | |
|  | <p>IR Drying</p> | <p>12 - 15 min. Follow the recommendations of the IR lamp manufacturer. Keep the flash-off time before drying</p> | |

:: STORAGE AND TRANSPORTATION CONDITIONS

Protect from freezing, heat, sunlight and moisture. Store tightly closed in a dry, cool place. Recommended storage and transportation temperature range is: +10 to +30°C. Avoid extreme temperature fluctuation.

Note: The storage and transportation temperature must be not lower than +5°C. Acclimatize the product to room temperature naturally.

:: REMARKS

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/cooling). It is not recommended to apply the product at a temperature below 18°C. Low application temperature changes the coating's properties and may impair the visual effect. Prior to application, the product temperature, spray booth temperature and object temperature should be adjusted to about 20°C.

:: SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions.

In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE