

:: Anti Rust Putty

anti corrosive putty

CHARACTERISTICS

A 2K polyester putty with integrated corrosion protection and excellent adhesion properties on steel and galvanized substrates. The filler can be applied and grinded in thin layers very easily for the protection of the substrates. The rust protection increases by 100% when using the Anti Rust Putty.

APPLICATION

A putty for the perfect rust prevention from the beginning. For all works which require an enhanced rust protection (e.g. guarantee service works)

- rust prevention guarantee
- oldtimer restoration
- colour red-brown
- easy to apply
- easy to sand
- very good adhesion

PRODUCT DATA

MATERIAL DATA:

Delivery viscosity at 20°C: pastelike

VOC content: 2004/42/IIB (b) (250) <250g/l

Colour: red-brown

Density: 1,8 - 1,9 g/cm³

.

HANDLING**SUBSTRATE**

The base must be clean, dry and grease-free. A good adhesion will only be reached on well sanded substrates.

DOSING

Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.

POT LIFE

At + 20°C room temperature: 5 minutes

REACTION TEMPERATURE

At least +5°C

APPLICATION

Spread on with a putty knife

DRYING

Air drying at +20°C room temperature, 16 - 30 minute

SANDABILITY

Following drying times given.

Hand or machine sanding - dry with P120 - P320

REWORKING

The fine putty can be gone over with the following CS products



12/2017

- Polyester putty
 - Spray or Spray plus
 - Washprimer
 - 1K Filler
 - High Build Primer
 - Filler 540
 - Filler vario
- or with all common 2K acrylic fillers, available on the market.

STORAGE

Approx 6 months at 18 - 20° C in closed original container.

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.



12/2017

Copyright VOSSCHEMIE