

:: Plastic Pro

plastic putty

CHARACTERISTICS

Plastic Pro is a polyester putty specially for the filling of plastic parts.

- advanced bulking agents
- very good adhesion properties
- perfect sanding
- very fine surface after sanding
- very high elasticity

APPLICATION

For repairing scratches and damages on polyester components.

When using PP it is necessary to use a primer before, only then you will reach a good putty adherence.

PRODUCT DATA

MATERIAL DATA:

Delivery viscosity at 20°C: paste like

V.O.C. content: 2004/42/II B (b) (250) < 250g/l

Colour: black

HANDLING

SUBSTRATE:

The base must be clean, dry and grease-free. A good adhesion can only be reached on well pre-sanded substrates.

DOSING:

Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.

POT LIFE:

At +20°C room temperature, 3 - 4 minutes.

REACTION TEMPERATURE:

At least +5°C.

APPLICATION:

Spread on with a putty knife.

DRYING TIME:

Air drying 15 minutes at a room temperature of +20°C

SANDING CHARACTERISTICS:

Following drying times given.

First sanding - dry with P150 - P180

Re-sanding - dry with P240 P360

REWORKING:

The Plastic Pro putty can be reworked with all common 2K acrylic fillers available in the market or with the following CARSYSTEM products:

- Plastic Cleaner
- Plastic Primer
- 1K Filler
- High Build Primer



04/2018

- Filler 540
- Filler vario

STORAGE:

Approx. 6 - 8 months at 18 - 20° C in closed original container

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE