

# CC.20 X-pert

2K clear coat

V03  
01/2025

## Characteristic

- 2K acrylic clear coat
- All-purpose clear coat
- Drying time: 30 - 35 min. / 40°C Object temperature - 20 min. / 60°C Objekttemperatur
- VOC conform

## Area of application

- All common paint work in a paint shop of individual parts up to a full vehicle
- It should be worked as quickly as possible when painting a full vehicle

## Benefits

- Fast drying time
- Very high final hardness
- Brilliant gloss

## Product Data

### Material data


Colour clear coat:	Transparent
V.O.C.:	2004/42/IIIB(d)(420) < 420 g/l
Shelf life:	12 month in closed original container at 20°C
Density clear coat at 20°C:	0.99 - 1.00 g/cm <sup>3</sup>
Density hardener at 20°C:	1.02 - 1.03 g/cm <sup>3</sup>
Dry film thickness:	50 - 60 µm
Efficiency:	10 - 12 m <sup>2</sup> /l

## Handling


For application on solvent-based or water-based paints. It is strongly recommended to work with the complete system. Drying and adhesion problems cannot be excluded with use of thinning and hardening materials of external systems.

Clear coat has to be reworked 2 hours after application at the latest.

### MIXING RATIO

	by volume		by weight	
	<b>CC.20 X-pert</b> <b>CC.20 X-pert hardener</b>	2 1		100 g 51 g








### SPRAYING VISCOSITY

	DIN cup 4mm bei 20°C	
	<b>Ford cup 4mm bei 20°C</b>	16 - 18 seconds
<b>ISO cup 4mm bei 20°C</b>	18 - 20 seconds	
	36 - 38 seconds	

# CC.20 X-pert

2K clear coat

V03  
01/2025

APPLICATION			
	<b>Spray gun gravity feed</b>	<b>Nozzle size / pressure</b>  Nozzle size: 1,2 - 1,3 mm Air pressure: Please pay attention to operating pressure recommendations of the manufacturer.	
	<b>Application</b>	<b>1,5 spraying operations</b>  1/2 thin closed coat 1 full wet coat	
	<b>Pot life at 20°C</b>	90 min	
	<b>Flash off</b>	5 - 10 minutes between coats 10 minutes before baking	
	<b>Dry coat thickness</b>	50 - 60 µm	
	<b>Process conditions</b>	Temperature 18 - 22°C Relative air humidity 40 - 60%	
	<b>Objekttemperatur</b>	<b>40°C</b>	<b>60°C</b>
	<b>Dry to polish</b>	30 - 35 min	20 min
	<b>IR Drying</b>	8 - 15 min. Follow the recommendations of the IR lamp manufacturer. Keep the flash-off time before drying	

# CC.20 X-pert

2K clear coat

V03  
01/2025



## Storage and Transportation Conditions

Protect from freezing, heat, sunlight and moisture. Store tightly closed in a dry, cool place. Recommended storage and transportation temperature range is: +10 to +30°C. Avoid extreme temperature fluctuation.

**Note:** The storage and transportation temperature must be not lower than +5°C. Acclimatize the product to room temperature naturally.



## Remark

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/ cooling). It is not recommended to apply the product at a temperature below 18°C. Low application temperature changes the coating's properties and may impair the visual effect. Prior to application, the product temperature, spray booth temperature and object temperature should be adjusted to about 20°C.

CARSYSTEM recommends to apply max. 2 coats.



## Safety Issues

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

© VOSSCHEMIE