

# Multi Green Changer

*Polyester multifunctional putty*

V03  
11/2024

## Description

- Polyester multifunctional putty
- Universal putty

## Area of application

- For filling small to deep imperfections, dents & scratches

## Benefits

- Colour change during the curing time from green to yellow
- Reduced surface moisture after curing
- Good balance between being semi-solid and creamy
- Multi adhesion

## Product Data

### Material data

Viscosity at 20°C:	paste-like
VOC-content:	2004/42/IIIB (b) (250) < 250 g/l
Density at 20 °C:	approx. 1.5 g/cm <sup>3</sup>
Colour:	green

## Handling

### Surface:

- The substrate must be clean, dry and free of grease
- Very good adhesion is reached on the below mentioned, coarsely sanded substrates

### Mixing instructions

- Addition of 2 % of hardener
- It is strongly recommended to avoid any over as well as underdosage of hardener. It can cause a lack of adherence and discolouration of the topcoat

### Pot-life:

- 4 - 5 minutes at +20 °C room temperature

### Reaction temperature:

- At least + 10 °C

### Hardening time:

- Drying time: 15 min / 20 °C object temperature

### Sanding:

- After the specified drying time  
Pre-sanding: dry with P80 - P150  
Re-sanding: dry with P150 - P240

### Reworking:

- The multifunctional putty can be reworked with all common polyester or acrylic-based materials

### Storage:

- ca. 6 - 8 months at 18 - 20° C in closed original container

## Information about adhesion

Steel	Aluminium	Galvanized tin	GRP	Plastic	2K Polyester putty	Wood
√	√	√	√	X	√	√

# Multi Green Changer

*Polyester multifunctional putty*

V03  
11/2024



## Safety issues

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

© VOSSCHEMIE