# TECHNICAL DATA SHEET



V06

05/2024

Multi Light

polyester multifunctional putty

# Description

- Multifunctional polyester putty
- Ultra lightweight putty

# Area of application

- For filling small to medium-sized imperfections, dents and scratches

# **Benefits**

Multi adhesion

# **Product Data**

### Material data

Viscosity at 20°C: as a paste VOC-content: 2004/42/IIB (b) (250) < 250g/ Colour: beige

# Handling

<u>Surface:</u>

- The substrate must be clean, dry and free of grease.
- Good adhesive properties on all roughly sanded bases.

### Dosing

- No more than 2-3% (by weight) of BPO hardener paste should be added to 100 parts of polyester filler.
- Excessive amounts of BPO hardener paste can cause a colour change of the topcoat.

## Pot-life:

At +20°C room temperature, 3-4 minutes

## Reaction temperature:

At least +5°C.

## Application:

Spread on with a spatula

### Hardening time:

Air drying at + 20°C room temperature, 20 - 30 minutes.

### Sanding:

After the specified drying time.

## Reworking:

 The Multi Light putty can be worked over with the following CS products - Elastic weiss or Elastic beige and Spray

### Storage:

- ca. 6 - 8 months at 18 - 20° C in closed original container

# Information about adhesion

Steel	Aluminium	galvanized tin	GRP	Plastic	2K Polyester putty	Wood
1	$\checkmark$	$\checkmark$	$\checkmark$	х	$\checkmark$	$\checkmark$

CARSYSTEM HEADQUARTERS VOSSCHEMIE GmbH Esinger Steinweg 50 25436 Uetersen / Germany Tel.: +49(0)4122/7170 www.carsystem.org



a trademark of

VOSSCHEMIE



Multi Light polyester multifunctional putty

V06 05/2024

•	Allow the product to reach the recommended application temperature naturally (avoid rapid
l	heating/ cooling). It is not recommended to apply the product at a temperature below 18 °C.
Notes	Low application temperature changes the coating's properties and may impair the visual

	The before mentioned technical data and information, especially the recommendations for					
	applying and using our products, are based on our current knowledge and experience when					
$\wedge$	applied under normal conditions. In practice, the materials, surfaces or site conditions are so					
	different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, expect we are					
	charged with intent or gross negligence. In this case the user is obliged to prove that he has					
SAFETY ISSUES	informed us about all points required for a proper and promising judgement in writing, in time					
	and completely. Patent rights of any third party are to be observed.					
	Furthermore, our general sales and delivery terms and conditions and the latest Technical Data					
	Sheet, which should be demanded, apply.					
	Directions for handling and waste disposal are in our Material Safety Data Sheet and the					
	specifications of the Employers Liability Insurance Association for the chemical industry.					
I	Copyright VOSSCHEMIE					

CARSYSTEM HEADQUARTERS VOSSCHEMIE GmbH

Esinger Steinweg 50 25436 Uetersen / Germany

Tel.: +49(0)4122/7170 www.carsystem.org



a trademark of

**WO**SSCHEMIE